



Ultra Foam Soft 2627

Description

This is the **standard foam core** for our **down & feather cushions**. It is commonly used where a **softer feel** is desired, such as for plush seat cushions where comfort is the primary requirement. Provides **good durability** and **resistance to sagging** over time for typical furniture use. Warranted to the original purchaser that it will give standard service in normal furniture and bedding applications. This **warranty is for 10 years** from the date of purchase. It will be necessary to submit your original document at the time a claim is initiated. Contact Albany Foam & Supply, 1355 Broadway, Albany, New York 12204. **This warranty may not be altered in any way.** Warranty limited to replacements only of Ultra Foam.

Typical Physical Properties

PROPERTY	TEST METHOD	TYPICAL RESULTS
Density – (lbs/Ft. ³)	ASTM D3574	2.38 – 2.63
25% IFD – (lbs)	ASTM D3574	25 - 31
Tensile Strength (min) (lbs/in ²)	ASTM D3574	10
Elongation % (min)	ASTM D3574	120
Compression Set @ 75% (max)	ASTM D3574	10
Compression Modulus (min)	ASTM D3574	1.9
Hysteresis Loss % (max)	ASTM D3574	30
Resiliency % (min)	ASTM D3574	40
Flammability	CAL TB117-2013	PASS

NB: Results are typical and do not encompass the entire range of values. The values have been supplied courtesy of VPC Group Inc.

Notice: The following details are accurate to the best of our knowledge as of the current date and are provided for informational purposes only. All polyurethane products, including modified versions, are combustible and will produce smoke and gas if ignited. The physical properties listed here should not be treated as formal specifications, as standard test results may vary within an expected range.

Data provided is based on specific, controlled laboratory test methods and may not reflect performance in actual fire conditions. Because these products are used in a wide variety of applications, we do not recommend specific uses or accept liability for the results or suitability of any particular application. This information is provided without any warranty, including implied warranties of merchantability or fitness for a particular purpose. Users are strongly encouraged to perform their own testing to determine safety and suitability for their specific needs."

IMPORTANT NOTICE REGARDING FLAMMABILITY

Fire resistance ratings are determined in laboratory settings and do not guarantee performance in real-world fire scenarios. Handle and store polyurethane foam carefully, ensuring it is always kept away from heat sources and open flames.

<https://Albanyfoam.com>



BIOFLX
SUSTAINABLE FOAM

Environmentally Sustainable



Includes Plant Material

*Revised 02/2026. This revision supersedes all previous publications.